

TECHNICAL FILTERS INC.

8815 CONROY WINDERMERE RD., ORLANDO, FL USA 32835

TEL: 407 217 2182

FAX: 407 217 2150

Web: www.technicalfilters.com

E-mail: info@technicalfilters.com

DATA SHEET

STYLE	APEXPES500	
CONSTRUCTION	POLYESTER WITH ePTFE MEMBRANE	
SCRIM	HIGH TENACITY SPUN SCRIM	
FINISH	HEAT SET, CALENDERED, SINGED ONE SIDE	
FILTRATION LAYER	ePTFE MEMBRANE	
WEIGHT, g/m ²	500 +/- 25	
THICKNESS, mm	1.7 – 1.9	
PERMEABILITY, l/dm ² .min @ 127 Pa	< 30	
TENSILE STRENGTH, N	WARP	> 1000
	WEFT	> 1200
ELONGATION AT BREAK, %	WARP	< 30
	WEFT	< 50
CONTINUOUS OPERATING TEMPERATURE, °C	130	
SURGE TEMPERATURE, °C	150	
SHRINGKAGE @ 150°C FOR 120 MINS, %	< 2.0	