

TECHNICAL FILTERS INC.

8815 CONROY WINDERMERE RD., ORLANDO, FL USA 32835

TEL: 407 217 2182

FAX: 407 217 2150

Web: www.technicalfilters.com

E-mail: info@technicalfilters.com

DATA SHEET

FABRIC	DURAVEYOR 4000-HD
APPLICATION	AIRSLIDES
FIBER	100% POLYESTER
CONSTRUCTION	NEEDED
FINISH	WATER REPELLENT
WEIGHT, g/m ²	4000
THICKNESS, mm	6.0
PERMEABILITY @ 127 PA, m ³ /m ² .hr	10
MULLEN BURST, mPa	60
WARP TENSILE STRENGTH, N	4200
WEFT TENSILE STRENGTH, N	4500
WARP MAXIMUM ELONGATION AT BREAK, %	35.0
WEFT MAXIMUM ELONGATION AT BREAK, %	45.0
CONTINUOUS OPERATING TEMPERATURE, °C	150
SURGE TEMPERATURE, °C	200
MOISTURE ABSORPTION @ 65 RH FACTOR AND 20°C, %	0.4