

# TECHNICAL FILTERS INC.

8815 CONROY WINDERMERE RD., ORLANDO, FL USA 32835

TEL: 407 217 2182

FAX: 407 217 2150

Web: [www.technicalfilters.com](http://www.technicalfilters.com)

E-mail: [info@technicalfilters.com](mailto:info@technicalfilters.com)

## DATA SHEET

FABRIC	DURAVEYOR4000	
APPLICATION	AIRSLIDES	
CONSTRUCTION	WOVEN POLYESTER	
TREATMENT	WATER REPELLENT	
WEIGHT, g/m <sup>2</sup>	4000	
THICKNESS, mm	4.5	
PERMEABILITY @ 127 PA, m <sup>3</sup> /m <sup>2</sup> .hr	10	
MULLEN BURST, mPa	65	
TENSILE STRENGTH, N [5*20 cm]	WARP	5600
	WEFT	5600
MAXIMUM ELONGATION AT BREAK, %	WARP	5.0
	WEFT	5.0
CONTINUOUS OPERATING TEMPERATURE, °C	150	
SURGE TEMPERATURE, °C	200	
MOISTURE ABSORPTION @ 65 RH FACTOR AND 20°C, %	0.1	