

TECHNICAL FILTERS INC.

8815 CONROY WINDERMERE RD., ORLANDO, FL USA 32835

TEL: 407 217 2182

FAX: 407 217 2150

Web: www.technicalfilters.com

E-mail: info@technicalfilters.com

DATA SHEET

STYLE	TFTF750	
CONSTRUCTION	PTFE FIBERS WITH STABILIZED PTFE SCRIM	
TREATMENT	ADVANCED PTFE HYBRID COATING	
WEIGHT, g/m ²	750	
THICKNESS, mm	1.0 – 1.4	
PERMEABILITY, L/dm ² .min @ 200 Pa	70 - 100	
TENSILE STRENGTH, N (5*20 cm)	WARP	> 800
	WEFT	> 800
ELONGATION AT BREAK, %	WARP	< 20
	WEFT	< 20
CONTINUOUS OPERATING TEMPERATURE, °C	260	
SURGE TEMPERATURE, °C	280	
SHRINKAGE AT 260°C FOR 90 MINS, %	WARP	< 3.0
	WEFT	< 3.0